



Aditya Birla Chemicals (Thailand) Ltd. (Epoxy Division)  
Grasim Industries Ltd. (Chemical Division)

### EPOTEC YD 515

#### Description

Epotec YD 515 is a bisphenol-A liquid epoxy resin modified with reactive diluent. This resin offers lower viscosity & lower surface tension. Both these properties are advantageous while formulating. The low viscosity improves the cost effectiveness by increasing filler loading & the low surface tension improves adhesion by better substrate wetting, it also helps in better pigment wetting and thereby improves the pigment dispersion and stability.

A wide variety of curing agents are available to cure this liquid epoxy resin at ambient conditions and also at elevated temperature. Sometimes systems based on this grade are post cured to improve certain characteristics such as glass transition temperature and chemical resistance.

#### Applications

- Self leveling floorings
- Trowelable mortars and grouts
- High solid and solvent free coatings
- Construction applications
- Adhesives

#### Specification

Appearance	Visual	Clear liquid
Colour	ASTM D 1544-04	0.5 G max.
Epoxy equivalent weight	ASTM D 1652-04	195 - 210 g/eq
Viscosity at 25°C	ASTM D 2196-05	600 - 900 cP

#### Typical properties\*

Epoxide value	4.76 - 5.13 eq/kg
Density @25°C	1.10 g/ml
Water content	0.1 % max.
Flash point	155 °C

\* Typical properties are indicated for information only

#### Packing

Epotec YD 515 is packed and delivered in steel drums, 220 kg per drum as a standard pack.  
Other packs are available on request.

**Storage**

Epotech YD 515 resin should be stored in original tightly closed container, in dry condition at room temperature (below 30°C). Under these conditions, it has a storage life of at least two years from the date of manufacturing.

Epotech YD 515 may become hazy or crystallize upon long storage especially when exposed to low temperatures. The resin can be restored to its original condition by warming to 55-60°C while stirring. For handling or pumping the maximum temperature recommended is 80°C.

---

**Handling**

Please refer to the MSDS of the product for more instructions on safe storage and handling of epotech YD 515.

**Disclaimer**

All recommendations for use of our products whether given by us in writing, verbally or to be implied from the results of tests carried out by us are based on the current state of our knowledge. Although, the information contained in this sheet is accurate, no liability can be accepted in respect of such information. We warrant only that our product will meet the designated specifications and make no other warranty either express or implied, including any warranty of merchantability or fitness for a particular purpose as the conditions of application are beyond our control.

**For Additional Information, Please Contact:**

**Aditya Birla Chemicals (Thailand) Ltd. (Epoxy Division)**

Mahatun Plaza Bldg., 16<sup>th</sup> Floor 888/167 Ploenchit Road, Lumpini, Bangkok 10330 Thailand

Tel: (662) 2535031-3, Fax: (662) 2535030

**Grasim Industries Ltd. (Chemical Division)**

Plot No.1, GIDC, Vilayat Industrial Estate, Tehsil Vagra, Dist. Bharuch – 392140, Gujarat, India

Tel: +91-8154007544

Web Site: [www.adityabirlachemicals.com](http://www.adityabirlachemicals.com), E-Mail: [epoxymktg@adityabirla.com](mailto:epoxymktg@adityabirla.com)